



Teflon®

Fluoropolymer

Teflon® FEP CJ 95 (previous code: TE 9335-N) Moulding and extrusion resin

Typical applications

Insulation and jacket for Wire and Cable, in applications demanding a high degree of stress crack resistance.

Description

Teflon® CJ 95 is one of DuPont's melt processable copolymers of tetrafluoroethylene and hexafluoropropylene.

It offers the excellent combination of properties characteristic of Teflon® fluoropolymer resins: non-ageing characteristics, chemical inertness, exceptional dielectric properties, heat resistance, toughness and flexibility, low coefficient of friction, non-stick characteristics, negligible moisture absorption and excellent weather resistance.

Teflon® CJ 95 is an intermediate molecular weight resin that possesses a high degree of stress crack resistance. It can be processed by conventional thermoplastic techniques, like melt extrusion.

Teflon® CJ 95 is a "high productivity" grade of Teflon® FEP. At processing temperatures it shows, compared to Teflon® 140-N, a lower viscosity and a higher critical shear rate. In similar constructions, it can be processed at much faster rates and higher extrusion line speeds, and the final product will show comparable physical properties. It can replace Teflon® 100-N for applications requiring a higher degree of stress crack resistance.

Stress crack resistance is an important element in establishing end-use performance. Extensive testing of wire and cable constructions is required for definitive performance evaluation. However, experience shows that the MIT folding endurance or flex life test, performed on a thin film of resin, has established a good correlation with extensive cable testing. The higher the MIT flex life, the higher the stress-crack resistance of the resin. The folding endurance of the high productivity grade Teflon® CJ 95, is marginally inferior to the one of the general purpose grade Teflon® 140-N. DuPont does however always recommend, in particular for applications involving repeated thermal and flex cycling, to undertake more extensive and more specific tests on the final cable itself. The MIT test results should be viewed as a guide to comparative performance of

the various grades of resin. See also DuPont's bulletin "Grade selector for Wire and Cable applications."

Teflon® CJ 95 will, according to material specification ASTM D 2116, fall into the category type I.

Processing

Teflon® CJ 95 fluoropolymer resin may be converted by conventional melt processing techniques, typical of those used for other thermoplastic resins.

The extruders and moulding machines used for Teflon® CJ 95 should be constructed of corrosion-resistant materials and be capable of operating at temperatures of 310-400°C.

Safety precautions

Industrial experience has proven that adequate ventilation, in properly maintained processing and handling areas, will eliminate known hazards to personnel. Resin containers should be opened and used in well-ventilated areas.

Equipment used to process at melt temperatures should be provided with local exhaust ventilation to completely remove all fumes and vapours from the processing area. In addition, care should be exercised to avoid the contamination of cigarettes and other forms of smoking tobacco when using fluoropolymer resins. Before using fluoropolymer resins, read the Material Safety Data Sheet (MSDS) and the detailed information in "Guide for the safe handling of Fluoropolymer Resins" published by APME. Copies can be obtained through your local DuPont representative.

Storage and handling

The properties of Teflon® CJ 95 resins are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and water condensation of the resin when it is removed from containers.

Packaging

Teflon® CJ 95 is packaged in 25 kg, single layer, plastic bags. For convenient shipment, orders of 500 kg pallets are recommended.

Typical Property Data for Teflon® FEP CJ 95 (previous code: TE 9335-N)

Property	Test method ¹⁾		Unit	Typical value
General				
Melt flow rate (MFR 372/5,0)	ISO 12086	D 2116	g/10 min	5
Specific gravity	ISO 1183	D 792	–	2,12-2,17
Bulk density	DuPont		g/l	1300
Mechanical				
Tensile strength, 23 °C	ISO 12086	D 638	MPa	26
Ultimate elongation, 23 °C	ISO 12086	D 638	%	300
Flexural modulus, 23 °C	ISO 178	D 790	MPa	655
Hardness, Shore durometer	ISO 868	D 2240	–	D-55
MIT folding endurance (0,18-0,20 mm film)			cycles	30000
Electrical				
Relative permittivity (60 Hz to 1 GHz)	IEC 250	D 150	–	2,1
Dissipation factor, tg δ (60 Hz to 1 GHz)	IEC 250	D 150	–	0,0002-0,001
Dielectric strength, short time	IEC 243	D 149		
0,25 mm film			kV/mm	>80
3,2 mm sheet			kV/mm	>15
Volume resistivity	IEC 93	D 257	Ω·m	>10 ¹⁶
Thermal				
Melting point	D 4591/D 3418		°C	255
Continuous service temperature ²⁾	–		°C	205
Rate of burning ³⁾	D 635		s	<5
			mm	5
Limiting Oxygen Index	ISO 4589	D 2863	%	>95
Specific heat capacity (20 °C)	C 177		J/(kg·K)	1090
Thermal conductivity (λ)	C 177		W/(m·K)	0,24
Other				
Chemical resistance	D 543		–	Excellent
Water absorption, 24 h	D 570		%	<0,01
Weathering resistance				Excellent

Note: Teflon® CJ 95 will, according to the material specifications ASTM D 2116, fall into the category Type I.
Typical properties are not suitable for specification purposes.

1) ASTM unless otherwise specified.

2) Definition of continuous service temperature:

The continuous service temperature is based on accelerated heat-ageing tests, and represents the temperature at which tensile strength and ultimate elongation retain 50% of the original values, after 20000 h thermal ageing. Continuous service temperature above 205 °C, may be feasible, depending on such factors as chemical exposure, support from the substrate, etc. Particularly when considering uses of Teflon® FEP CJ 95 above 205 °C, preliminary testing should be done to verify suitability.

3) These results are based on laboratory tests, under controlled conditions, and do not reflect performance under actual fire conditions.

For further information contact:

Deutschland

Du Pont de Nemours (Deutschland) GmbH
DuPont Straße 1
D-61352 Bad Homburg v.d.H.
Tel. (06172) 87 0
Telefax (06172) 87 13 18

France

Du Pont de Nemours (France) S.A.
137, rue de l'Université
F-75334 Paris Cedex 07
Tel. 01 45 50 65 50
Telefax 01 45 50 61 51

Italia

Du Pont de Nemours Italiana S.p.A.
Via A. Volta, 16
I-20093 Cologno Monzese (Mi)
Tel. (02) 25 30 21
Telefax (02) 25 47 765

Nederland

Du Pont de Nemours (Nederland) B.V.
Baanhoekweg 22
NL-3313 LA Dordrecht
Tel. (078) 630 10 11
Telefax (078) 630 16 77

United Kingdom

Du Pont (U.K.) Limited
Maylands Avenue
GB-Hemel Hempstead,
Herts. HP2 7DP
Tel. (01442) 21 85 00
Telefax (01442) 21 85 75

Requests for further information from countries not listed above should be sent to:

Du Pont de Nemours International S.A.

2, chemin du Pavillon
CH-1218 Le Grand-Saconnex, Geneva
Tel. (022) 717 51 11
Telefax (022) 717 54 11

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement", H-51459.

Brand: The Teflon® trademark may only be used under licensing agreement granted by DuPont for use in approved applications.



Teflon®

Only by DuPont