



MONPRENE® THERMOPLASTIC ELASTOMER

Typical Property Values - MONPRENE MP-1900					
PROPERTY*	TEST METHOD	TYPICAL VALUES	TEST UNITS	TYPICAL VALUES	TEST UNITS
INSTANTANEOUS HARDNESS	ASTM D-2240	50	Shore 00		
SPECIFIC GRAVITY	ASTM D-792	0.87			
TENSILE STRENGTH	ASTM D-412	300	psi	2.1	MPa
ULTIMATE ELONGATION	ASTM D-412	700	%		
MELT INDEX CONDITION B 125°C/2.16 KG	ASTM D-1238	10	g/10 min		
TENSILE MODULUS @ 300%	ASTM D-412	50	psi		

*Not to be construed as specification.

Teknor Apex Thermoplastic Elastomers

Corporate Headquarters

505 Central Avenue
Pawtucket, RI 02861 USA
Web: www.teknorapex.com
E-mail Us: tpe@teknorapex.com
Phone: 401-725-8000 – Toll Free: 866-438-8737
Fax: 401-728-5680

Vermont Operations

300 Industrial Park Road
St. Albans, VT 05478 USA
Phone: 802-524-7704
Toll Free: 888-778-8737
Fax: 802-524-7680

Kentucky Operations

3070 Ohio Drive
Henderson, KY 42440 USA
Phone: 866-438-8737
Fax: 401-728-5680

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own test to determine the suitability of such products for their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.