



## MONPRENE® THERMOPLASTIC ELASTOMER

Typical Property Values - MONPRENE MP-3005-L3					
PROPERTY*	TEST METHOD	TYPICAL VALUES	TEST UNITS	TYPICAL VALUES	TEST UNITS
INSTANTANEOUS HARDNESS	ASTM D-2240	53	Shore A		
SPECIFIC GRAVITY	ASTM D-792	0.89	g/cc		
TENSILE STRENGTH	ASTM D-412	1,200	psi	8.3	MPa
ELONGATION AT BREAK	ASTM D-412	700	%		
MELT INDEX CONDITION G 200°C/5.0 KG	ASTM D-1238	1.5	g/10 min		
TENSILE MODULUS @ 300%	ASTM D-412	300	psi	2.1	MPa
COMPRESSION SET 23°C 70°C	ASTM D-395B	18.0 57.0	% %		

\*Not to be construed as specification.

### Teknor Apex Thermoplastic Elastomers

#### Corporate Headquarters

505 Central Avenue  
Pawtucket, RI 02861 USA  
Web: [www.teknorapex.com](http://www.teknorapex.com)  
E-mail Us: [tpe@teknorapex.com](mailto:tpe@teknorapex.com)  
Phone: 401-725-8000 – Toll Free: 866-438-8737  
Fax: 401-728-5680

#### Vermont Operations

300 Industrial Park Road  
St. Albans, VT 05478 USA  
Phone: 802-524-7704  
Toll Free: 888-778-8737  
Fax: 802-524-7680

#### Kentucky Operations

3070 Ohio Drive  
Henderson, KY 42440 USA  
Phone: 866-438-8737  
Fax: 401-728-5680

The information and suggestions contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's suggestions. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.