

Wynca Tinyo Silicone Co.,Ltd

General PurposeSilicone Rubber

TY4366-70

BRIEF

- general purpose type heat cured compounds for extrusion.

MODEL

- TY4366-70

KEY FEATURES

- Extruded molding Type
- Excellent mechanical properties
- Formulated to meet FDA 21 CFR 177.2600
- Formulated to meet LFGB

APPLICATIONS

- Tubing
- Wires, cable

HANDING,SAFETY AND STORAGE

- Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information.
- The material safety data sheet is available on the Wynca Tinyo Silicone CO.,LTD website at www.Wynca.com. You can also obtain a copy from your local Wynca Tinyo sale representative.
- When stored at or below 38°C in the original unopened containers, this product has a usable life of 6 months from the data of production;Please put to use within 3 months had better.

PACKAGING

- 20kg box

Address: Yingfu Industrial Park,High-tech Industrial Development Zone,Qingyun

Tel: (+86763)3608674

Fax: (+86763)3608669

Website: www.wynca.com

Postcode: 511500

Wynca Tinyo Silicone Co.,Ltd

General Purpose Silicone Rubber

TY4366-70

TYPICAL PROPERTY DATA

Test Item	Unit	Value
appearance	--	translucent
plasticity	0.01mm	270±40
density	g/cm ³	1.21±0.05
authentication FDA	--	pass
authentication ROHS	--	pass
tensile strength	MPa	≥5
tensile set	%	≤8
elongation	%	≥200
tear strength B	N/mm	≥10
hardness	HA	69±3

- Specification writers: These values are not intended for use in preparing specifications. Please contact your local TIANYU sales representative prior to writing specification on this product.
- Properties obtained : Press cured 10 minute at 120°C, 1.3% catalyst: .2,4-dichlorobenzoyl peroxide.

Issued 2012-06-2

For industrial use only

It is responsibility of the user to determine the suitability of any Wynca Tinyo Silicone CO.,LTD PROUCT FOR IMPLANTATION OR INJECTION INTO THE HUMAN BODY.

Specifications are available by contacting Wynca Tinyo Silicone CO.,LTD. Typical property data values should not be used as specification. Inasmuch as Wynca Tinyo Silicone CO.,LTD. Has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained.

Each user of the material should make his own tests to determine the suitability of the material for his own particular use. Statements concerning possible or suggested uses of the material described herein are not to be construed as constituting a license under any Wynca Tinyo Silicone CO.,LTD.

Address: Yingfu Industrial Park, High-tech Industrial Development Zone, Qingyun

Tel: (+86763)3608674

Fax: (+86763)3608669

Website: www.wynca.com

Postcode: 511500