

Data Sheet

Novapex PPC4oLF G

Description

Novapex PPC4oLF is premium 40% CaCO₃ reinforced polypropylene thermoplastic moulding compound. It has a good balance of mechanical and physical properties together with easy flow characteristics, good UV stability and heat stability. This grade is custom coloured to match traffic gray RAL7043.

End Use /Process

Injection moulding for various industrial and commercial parts and products.

Properties		Value	Test Method
Novapex PPC4oLF G			
Density (g/cm ³)		1.18	ISO 1183 Method A
MFI	(g/10 min)	18.7	ISO 1133
MFR	(cm ³ /10 min)	15.8	ISO 1133
Ash content (%)		29.4	ISO 3451-1 Method A
Tensile test – strength & elongation	Strain at peak (%)	2.42	ISO 527
	Stress at peak (MPa)	16.3	ISO 527
	Strain at break (%)	15.2	ISO 527
	Stress at break (MPa)	13.4	ISO 527
Izod impact test	Notched (kJ/m ²)	11.57	ISO 180/1A
	Unnotched (kJ/m ²)	102.3	ISO 180/1A
Flexural analysis	Load at yield (k/N)	0.05	ISO 178
	Stress at yield (MPa)	30.8	ISO 178
	Modulus (MPa)	1389	ISO 178

Disclaimer

This information is not to be taken as warranty or representation for which we assume legal responsibility nor a permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, verification and shall form no part of any contract with customer.

Additional Information

Our Contact Details:

21 Chenik street
Chamdor
1739

Tel: 011 025 7125
Fax: 011 762 1595
Email: sunette@xplic.co.za

Website: www.xuba.co.za
Published: 6/8/2016