



TAISAP SUPERABSORBENT POLYMERS

Formosa Plastics Corporation

Tairylan Division

RM 175, 4TH FLR, 201, Tung Hua North Road, Taipei, Taiwan

Tel: +886-2-27178136 Fax: +886-2-27134818

BC 8000 TECHNICAL DATA

Product Name	TAISAP BC 8000			
Chemical Basis	Sodium Polyacrylate			
Appearance	White granules			
Specified Characteristic	Unit	Min.	Max.	Test method
Apparent Bulk Density	g/L	580	700	12C00.sap.017 (WSP 251.0)
Centrifuged Retention Capacity	g/g	36		12C00.sap.013 (WSP 241.2)
AAP 0.7psi	g/g	20		12C00.sap.015 (WSP 242.2)
pH value		5.6	6.5	12C00.sap.008 (WSP 200.2)
Particle Size Distribution				12C00.sap.010 (WSP 220.2)
>850 μ m/ 20mesh	%		1	
>600 μ m/ 30mesh	%	10	45	
>300 μ m/ 50mesh	%	30	70	
>150 μ m/ 100mesh	%	5	30	
<150 μ m/ 100mesh	%		5	
Moisture Content	%		7	12C00.sap.011 (WSP 230.2)

Effective date
2018/1/28

Issue date
2018/1/28

Approval date
2018/1/28

FPC Tairylan SAP QA approved

BC8000 (DATE20180128)